

# Mafill® CR X 8049 terracotta L004

Polypropylene  
Industrial Quality Compound

## Description:

PP compound, terracotta

## General

MFI (230°/2,16kg)	ISO 1133	30	g/10min
Density	ISO 1183	0.97	g/cm <sup>3</sup>

## Thermal

Vicat A50	ISO 306	130	°C
-----------	---------	-----	----

## Mechanical

Izod notched impact strength (23°C)	ISO 180	4.50	kJ/m <sup>2</sup>
Tensile modulus	ISO 527	1200	MPa
Flexural modulus	ISO 178	850	MPa

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. Ravago industrial quality compounds are totally or partially produced with non-prime quality ingredients. Even though the selection of the raw materials, the production and the quality control is being done following to the common best practices, it is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

## Ravago Group Headquarters

Moerenstraat 85A  
B - 2370 Arendonk

Tel: +32 (0)14 67 25 11  
Fax: +32 (0)14 67 20 12

www.ravago.com  
manufacturing@ravago.com

Issue Date:  
Nov 2008